

**A M E N D M E N T S**

**AMENDMENTS TO THE CLAIMS**

1. (Withdrawn-Currently amended) A method comprising ~~a plurality of activities comprising:~~  
providing a ~~solution~~composition comprising water and a dispersion of solid particles comprising ~~a~~an internally ~~substantially~~ crosslinked polymer comprising at least one hydrophobic substituent and N-isopropyl acrylamide, wherein the polymer releases heat over a range of dropping ambient temperatures beginning at about 4.4 degrees C; and  
coating at least a portion of a surface of a plant with the ~~solution~~composition.
2. – 14. (Canceled)
15. (Withdrawn) The method of claim 1, wherein the particles are nanoparticles.
16. (Withdrawn) The method of claim 1, wherein each of the particles has a molecular weight of from about 500,000 to about 50,000,000.
17. (Withdrawn) The method of claim 1, wherein the particles have an average diameter of from about 2 nanometers to about 1000 nanometers.
18. – 66. (Canceled)

67. (Withdrawn-Currently amended) A method comprising ~~a plurality of activities comprising:~~  
providing a ~~solution~~ composition comprising water and a dispersion of solid particles comprising ~~a~~ an internally ~~substantially~~ crosslinked polymer comprising at least one hydrophobic substituent and N-isopropyl acrylamide, wherein the polymer releases heat over a range of dropping ambient temperatures beginning at about 4.4 degrees C;  
coating at least a portion of a surface with the ~~solution~~ composition; and  
preventing the formation of ice on the surface.
68. (Withdrawn-Currently amended) A method comprising ~~a plurality of activities comprising:~~  
polymerizing at least one hydrophobic substituent and N-isopropyl acrylamide to form solid nanoparticles having an average diameter of from about 11 nanometers to about 450 nanometers, the nanoparticles comprising ~~a~~ an internally ~~substantially~~ crosslinked polymer comprising the at least one hydrophobic substituent and ~~the~~ N-isopropyl acrylamide, wherein the polymer releases heat over a range of dropping ambient temperatures beginning at 4.4 degrees C; and  
forming a ~~solution~~ composition comprising water and a dispersion of the solid nanoparticles; and  
coating at least a portion of a surface of a plant with the composition.
69. (Currently amended) A composition comprising:  
an aqueous ~~solution comprising a~~ dispersion of solid particles comprising an internally ~~substantially~~ crosslinked polymer comprising at least one hydrophobic substituent and ~~the~~ N-isopropyl acrylamide, wherein the polymer releases heat over a range of dropping ambient temperatures beginning at 4.4 degrees C, the composition adapted to form a coating over at least a portion of a surface of a plant, the coating weighing from about 0.5% to about 3% of a weight of a coated portion of the plant.

70. (Withdrawn-Currently amended) A composition comprising:  
water droplets comprising a dispersion of solid particles comprising an internally  
~~substantially~~ crosslinked polymer comprising at least one hydrophobic substituent  
and ~~the~~ N-isopropyl acrylamide, wherein the polymer releases heat over a range of  
dropping ambient temperatures beginning at 4.4 degrees C, the composition adapted  
to be coated on at least a portion of a surface of a plant.
71. (Previously Presented) The composition of claim 69, wherein the polymer releases  
heat over a range of dropping ambient temperatures ending at about -3.89 degrees C.
72. (Currently amended) The composition of claim 69, wherein the ~~hydrophilic monomer~~  
N-isopropyl acrylamide is water soluble.
73. (Canceled)
74. (Previously Presented) The composition of claim 69, wherein the particles are  
nanoparticles.
75. (Previously Presented) The composition of claim 69, wherein each of the particles has  
a molecular weight of from about 500,000 to about 50,000,000.
76. (Previously Presented) The composition of claim 69, wherein the particles have an  
average diameter of from about 2 nanometers to about 1000 nanometers.
77. – 81. (Canceled)
82. (Previously Presented) The composition of claim 69, wherein the particles have an  
average diameter of less than about 200 microns.

83. (Withdrawn) The composition of claim 70, wherein the water droplets are coated with a hydrated polymer gel.
84. (Withdrawn) The composition of claim 70, wherein the water droplets are coated with a hydrated polymer gel that, when applied to at least a portion of a surface of a plant, releases heat over a range of dropping ambient temperatures beginning at about 35 degrees F.
85. (Withdrawn-Currently amended) A composition comprising:  
a foam comprising an aqueous ~~solution comprising a~~ dispersion of solid particles comprising an internally ~~substantially~~ crosslinked polymer comprising at least one hydrophobic substituent and ~~the~~ N-isopropyl acrylamide, wherein the polymer releases heat over a range of dropping ambient temperatures beginning at 4.4 degrees C.
86. (Withdrawn) The composition of claim 85, wherein the foam comprises a hydrated polymer gel.
87. (Withdrawn) The composition of claim 85, wherein the foam comprises air bubbles.
88. (Withdrawn) The composition of claim 85, wherein the foam comprises air bubbles having a diameter in the range of from about 10 microns to about 100 microns.